



# HVIS High voltage insulation sheets Voltage class 36 kV Max. busbar width 150 mm

#### **Product description**

HVIS is an adhesive coated, heatshrinkable sheet which provides insulation enhancement and protection against accidently induced discharge. When heated the HVIS sheet shrinks in two directions to tightly conform to complex shapes. A Raychem void-filling mastic, \$1061, can be added to ensure that even protruding shapes are insulated. A Raychem sealing mastic, S1085, can also be applied to provide an environmentally sealed connection. The sheet can be cut to size on site and loosely secured in place with clamps and brackets available from us. Once installed, the clamps and brackets can be removed and re-used. HVIS sheet will provide flashover protection up to 17.5 kV or up to 25 kV if the void-filling mastic is applied underneath the sheet, or up to 36 kV if a double layer of HVIS is used. Re-usable joint covers can also be made to allow access or maintenance when required.

### **Applications**

HVIS sheet will cover almost any size or shape of busbar joint, making it ideal for insulating busbar tees, elbows and other connections where tubing and tape cannot be used.

## **Clearance reduction**

The table below indicates the clearance reductions which are possible using HVIS sheet. These are derived from BIL, AC withstand, DC withstand and discharge extinction tests. These clearances should not be adopted without testing by the user. Sharp electrodes and unusual geometries may require wider clearances.



Rated voltage	Phase – phase	Phase – ground	IEC 71-2 air clearance					
(kV)	(mm)	(mm)	(mm)					
Round b	usbars							
12	55	65	120					
17.5	70	85	160					
24	95	125	220					
36	150	205	320					
Rectang	Rectangular busbars							
12	65	75	120					
17.5	85	104	160					
24	115	150	220					
36	200	285	320					

# Features/benefits

- Compatible with all other products in the Raychem MV insulation enhancement system
- Easy to install on site using a gas torch or hot air device
- Manufactured from a non-halogen based material, noxious and corrosive effects are greatly reduced in the event of a fire
- Excellent anti-tracking properties
- Excellent UV and weather resistant properties make HVIS suitable for indoor or outdoor use
- Can be stored indefinitely at temperatures up to 50°C without loss of performance




Key product specifications	Test method	Requirement
Dielectric strength	ASTM D149, IEC 243	130 kV/cm min. @ 2 mm
Accelerated ageing	ISO 188, ASTM D2671	168 hrs @ 120°C
-Tensile strength		10 MPa min.
- Ultimate elongation		300% min.
Low temperature	ASTM D2671	No cracking
flexibility	Procedure C	after 4 hrs @ -40°C
Comparative tracking index	VDE 0303/1	KA 3c
Smoke index	NES 711	Less than 50
Acid gas generation	Raychem PPS 3010 4.23	Less than 2% by weight
Resistance to transformer oil	VDE 0370	168 hrs @ 23°C
-Tensile strength		7.5 MPa min.
- Ultimate elongation		300% min.

Note: For further product specification information see Raychem PPS 3010/25. The above information refers to backing material only, for adhesive requirements see PPS 3012/43. For void-filling mastic S1061 requirements see PPS 3012/13, for sealing mastic S1085 requirements see PPS 3012/3.

#### **Product selection**

For rectangular busbars max. thickness 15 mm





-							
	-c	ΛI	าท	e	cti	ΛI	n


## Flat elbow connection

	1-0011116011011			i lat elbow confilection			
		No. of installations per			No. of installations per		
	Cut size	HVIS-05	HVIS-10	Cut size	HVIS-05	HVIS-10	
<b>Busbar width</b>	needed (mm)	sheet	rolls	needed (mm)	sheet	rolls	
25	275 x 225	4	88	275 x 175	4	114	
50	325 x 250	4	80	325 x 225	4	88	
75	400 x 275	2	50	325 x 250	2	52	
100	450 x 325	2	44	450 x 275	2	44	
175	550 x 425	1	23	550 x 325	1	30	

Note: This table should be used as a guideline only. Please experiment with one or two joints before adopting final cut size. The busbars are assumed to be insulated to 25 mm from the joint. Cut size should extend a minimum of 100 mm on each leg of the joint before shrinking and should overlap existing insulation by 65 mm after shrinking.

#### **Ordering information**





Ordering description	Dimensio P a (m) nom.	ons Q a nom.	W₁ b min.	W <sub>2</sub> a min.	UOM	
HVIS-05	0.5	660	1.5	2.4	sheet	
HVIS-10	10.0	660	1.5	2.4	roll	
S1061-8-300	0.3	60	-	-	piece	
S1085-1-300	0.3	20	=	-	piece	
HVIS-TOOLS-01	(basic clan	np and bracket kit)			kit	
HVIS-TOOLS-02	(extended	clamp and bracket k	cit)		kit	

Note: Dimensions in mm unless otherwise stated. a = as supplied b = after free recovery. Longitudinal and transverse change after free recovery: -25 % ±10%. Installation instructions EPP 0623 5/96 and Material Safety Data Sheet available on request. When required, typically one piece of sealing mastic, S1085, is applied on each leg of the joint and one or two pieces of voidfilling mastic, S1061, used to cover uneven shapes.

#### **Technical reports**

# UVR 8114 - Qualification report for HVIS

All of the above information, including drawings, illustrations and graphic designs, reflects our present understanding and is to the best of our knowledge and belief correct and reliable. Users, however, should independently evaluate the suitability of each product for the desired application. Under no circumstances does this constitute an assurance of any particular quality or performance. Such an assurance is only provided in the context of our product specifications or explicit contractual arrangements. Our liability for these products our standard terms and conditions of sale. ALR, AMP, AXICOM, B&H, BOWTHORPE EMP, CROMPTON INSTRUMENTS, DORMAN SMITH, DULMISON, GURO, HELLSTERN, LA PRAIRIE, MORLYNN, RAYCHEM, and SIMEL are trademarks.



















Energy Division - a pioneer in the development of economical solutions for the electrical power industry. Our product range includes: cable accessories, connectors & fittings, electrical equipment, instruments, lighting controls, insulators & insulation enhancement and surge arresters.

















